






Dimensions mm[inch]

tolerances acc. to DIN ISO 2768-m
Toleranzen gem. DIN ISO 2768-m

Isometric

Scale 2:1
Maßstab 2:1



Mag. values DIN IEC 60404-8-	Conditions	Min	Typ	Max	Unit
Magnet Material		Samarium Cobalt			
Remanent Induction Br		900	925		mT
Revers. temp. coeff. of Br				-0,042	%/K
Coercivity HcB		680	710		kA/m
Intrinsic Coercivity HcJ		1.750	2.000		kA/m
Max. operating temperature				250	°C
Magnetic moment	inclusive of 5% tolerance	6,8	7,1	7,3	E-6 Vs*cm
Direction of Magnetization		axial			
Density			8,3		g/cu cm

General data	Conditions	Min	Typ	Max	Unit
Remarks		all details acc. to supplier informations.			

AMEYA360

Components Supply Platform

Authorized Distribution Brand :



Website :

Welcome to visit www.ameya360.com

Contact Us :

➤ Address :

401 Building No.5, JiuGe Business Center, Lane 2301, Yishan Rd
Minhang District, Shanghai , China

➤ Sales :

Direct +86 (21) 6401-6692

Email amall@ameya360.com

QQ 800077892

Skype ameyasales1 ameyasales2

➤ Customer Service :

Email service@ameya360.com

➤ Partnership :

Tel +86 (21) 64016692-8333

Email mkt@ameya360.com