

- **■** Resists Snagging
- Prevents Damage From UV, Gasoline, Engine Chemicals And Salt
- Resists Cut, Abrasion And Penetration
- Flexible & Economical General Purpose Protection
- Deflects High Pressure Hose Ruptures
- **Custom Lengths Available**



W.		4 -		_ [
W	r, i	te	ri	וה
-			-	_

Nylon

Grade

DFN

Wall Thickness

.045"

Drawing Number

TF001DF-WD



Nominal Size	Part #	Wall Thickness	Maxi Coil	Bulk Spool	Shop Spool	Available Colors	Lbs/ 100'
0.71"	DFN0.71BK	.045"	300′	100′	50′	Black	2.57
0.83"	DFN0.83BK	.045"	300′	100′	50′	Black	2.58
0.92"	DFN0.92BK	.045"	300′	100′	50′	Black	3.22
1.00"	DFN1.00BK	.045"	300′	100′	50′	Black	3.66
1.13"	DFN1.13BK	.045"	300′	100′	50′	Black	4.18
1.25"	DFN1.25BK	.045"	300′	100′	50′	Black	4.49
1.34"	DFN1.34BK	.045"	300′	100′	50′	Black	4.84
1.59"	DFN1.59BK	.045"	300′	100′	50′	Black	5.37
1.75"	DFN1.75BK	.045"	300′	100′	50′	Black	6.13
2.07"	DFN2.07BK	.045"	300′	100′	50′	Black	7.26
2.38"	DFN2.38BK	.045"	300′	100′	50′	Black	8.28
2.54"	DFN2.54BK	.045"	300′	100′	50′	Black	8.98
2.86"	DFN2.86BK	.045"	300′	100′	50′	Black	9.89
3.34"	DFN3.34BK	.045"	300′	50′	25′	Black	11.59
3.66"	DFN3.66BK	.045"	300′	50′	25′	Black	12.25


Industrial Hose And Cable Protection For Harsh Environments

The tightly woven Nylon® makes DF the perfect solution for hose & cable protection. The .045 inch wall thickness will protect cables, hoses and ropes from weather, sunlight and abrasion damage.

When installed over uncoated cable or chains, DF will prevent scraping, chafing and contact damage to painted or other fragile surfaces. DF is resistant to chemicals, UV damage and rot, and is suitable for continuous outdoor use under all weather conditions.

The flexible sleeving cuts with a scissor and the tight construction slides easily over any application.

This is a non-expandable product. Be sure to match your application diameter accurately.



■¬ Colors Available:



104 Demarest Road • Sparta, NJ 07871





Abrasion Resistance High

Abrasion Test Machine
Taber 5150

Abrasion Test Wheel
Calibrase H-18

Abrasion Test Load 500g

Room Temperature 80°F

Humidity **70**%

Visible Wear And Some Pulling Of Fibers 500 Test Cycles

Further Wear And Some Pulling At Seam 550 Test Cycles

Material Wearing Through At Seam 2,750 Test Cycles

Material Destroyed 3,500 Test Cycles

Pre-Test Weight 7,191.6 mg

Post-Test Weight 6,680.7 mg


Test End Loss Of Mass Point Of Destruction 510.9 mg



1=No Effect 2=Little Effect 4=More Affected 5=Severely Affected

3=Affected

Aromatic Solvents ______ 1 Aliphatic Solvents______ 1 Chlorinated Solvents ______ 1 Weak Bases 1 Salts Strong Bases ______ 2 Salt Water *0-S-1926*_______1 Hydraulic Fluid MIL-H-5606 ______ 1 Lube Oil MIL-L-7808 De-Icing Fluid *MIL-A-8243* ______ 1 Strong Acids ______5 Strong Oxidants ______ 5 Esters/Ketones ______ 1 UV Light ______ 2 Petroleum 3 Fungus *ASTM G-21* ______ 2 Halogen Free Yes RoHS Yes



PHYSICAL PROPERTIES

Monofilament Diameter ASTM D-204	NA
Recommended Cutting	Scissor
Colors	1
Wall Thickness	045
Specific Gravity ASTM D-792	1.14
Moisture Absorption % ASTM D-570	2.7
Hard Vacuum Data ASTM E-595 at 10-5 torr	
TML	1.10
CVCM	.01
WVR	69
Outgassing	High
Oxygen Index	22
ASTM D-2863	

© 2016 Techflex, Inc. - Any unauthorized reproduction, in whole or part, in any medium whatsoever, without the express written permission of Techflex, Inc. is strictly forbidden.

AMEYA360 Components Supply Platform

Authorized Distribution Brand:

























Website:

Welcome to visit www.ameya360.com

Contact Us:

Address:

401 Building No.5, JiuGe Business Center, Lane 2301, Yishan Rd Minhang District, Shanghai , China

> Sales:

Direct +86 (21) 6401-6692

Email amall@ameya360.com

QQ 800077892

Skype ameyasales1 ameyasales2

Customer Service :

Email service@ameya360.com

Partnership :

Tel +86 (21) 64016692-8333

Email mkt@ameya360.com