

*** UNCONTROLLED DOCUMENT * FOR REFERENCE ONLY**

STEWARD		CORE DIMENSIONS							
	UNCOATED CORE		35T0375-100						
		MM	INCHES	MM	INCHES				
	OD	9.53	(.375)	± .25	(.010)				
	ID	4.75	(.187)	± .25	(.010)				
	TH	3.18	(.125)	± .13	(.005)				
EPOXY COATING		35T0375-10H							
	OD	10.55	(.415)	±	max				
	ID	3.73	(.147)	±	min				
	TH	4.07	(.160)	±	max				
WEIGHT / K		0.9072 KGS		2.0000 LBS					
INITIAL PERMEABILITY		5000							
ELECTRICAL SPECIFICATIONS									
		MIN		NOM	MAX	MAX	FREQ.	VOLT.	
		(μH)	MIN TOL.	(μH)	(μH)	TOL.	(kHz)	(V)	TURNS
L1		1.772	(-20%)	2.214	2.657	+20%	100	≤ .0032	1
L2		177.2	(-20%)	221.4	265.7	+20%	100	≤ .0324	10
Q		10	-	-	-	-	100	≤ .0032	1
COATING SPECIFICATIONS									
		Max. Coating Thickness			TEST FORCE				
	TYPE	(mm)	Min. DLB VAC	Min. DLB VDC	(LB)				
35T0375-100	UNCOATED	-	-	-	-				
35T0375-10H	EPOXY	0.76	1000	1333	.83				
NOTES									

Steward

THIS DOCUMENT CONTAINS INFORMATION WHICH IS PROPRIETARY TO STEWARD. NO PRODUCTION OR PUBLICATION OF THIS DOCUMENT IN WHOLE OR IN PART SHALL BE MADE WITHOUT WRITTEN AUTHORIZATION FROM STEWARD.

Date:	01/05/2006	DWG #:	35T0375-10H-C	Title:	35T0375-10H	REV:	C
Drawn By:	JRK						

REV	Description	ECN #	Date	INT
C	CHANGE COATING DESCRIPTION FROM POLYURETHANE ADD KGS TO WEIGHT		01/05/2006	JRK

AMEYA360

Components Supply Platform

Authorized Distribution Brand :



Website :

Welcome to visit www.ameya360.com

Contact Us :

➤ Address :

401 Building No.5, JiuGe Business Center, Lane 2301, Yishan Rd
Minhang District, Shanghai , China

➤ Sales :

Direct +86 (21) 6401-6692

Email amall@ameya360.com

QQ 800077892

Skype [ameyasales1](#) [ameyasales2](#)

➤ Customer Service :

Email service@ameya360.com

➤ Partnership :

Tel +86 (21) 64016692-8333

Email mkt@ameya360.com